## RECEIVED CENTRAL FAX CENTER

T-050 P.004/015 F-069

Serial No. 10/806,318

OCT 1 3 2006

Docket No. 1293.1278C4

## IN THE SPECIFICATION:

Please amend paragraph 0044 as follows

[0044] Table 2 shows parameters of thin films of the optical disc used in another simulation for interpreting heat.

Table 4Table 2

Material	λ = 405nm		C(J/cm <sup>3</sup> K)	k(W/cmK)
	n	K		
ZnS-SiO2	2.300	0.000	2.055	0.0058
Sb-Te eutectic	1.650	3.150	1.285	0.0060
(Crystal)				
Sb-Te eutectic	2.900	2.950	1.285	0.0060
(Amorphous)				
Ag alloy	0.170	2.070	2.450	0.2000